

Chapter 43

Practical Applications of X-Ray Line Profile Analysis

Jenő Gubicza

Eötvös Loránd University, Hungary

ABSTRACT

In the previous chapters, the theory and the main methods of diffraction peak profile analysis were presented. Additionally, the specialties in the measurement and the evaluation of line profiles in the cases of thin films and single crystals were discussed. In this chapter, some practical considerations are given in order to facilitate the evaluation of peak profiles and the interpretation of the results obtained by this method. For instance, the procedures for instrumental correction are overviewed. Additionally, how the prevailing dislocation slip systems and twin boundary types in hexagonal polycrystals can be determined from line profiles is shown. Besides the dislocation density, the vacancy concentration can also be obtained by the combination of electrical resistivity, calorimetric, and line profile measurements. The crystallite size and the twin boundary frequency determined by X-ray peak profile analysis are compared with the values obtained by the direct method of transmission electron microscopy. Furthermore, the limits of line profile analysis in the determination of crystallite size and defect densities are given. Finally, short overviews on the results obtained by peak profile analysis for metals, ceramics, and polymers are presented.

INTRODUCTION

The experimental settings of the X-ray diffractometer used in the measurement of line profiles and the preparation of the data before evaluation (e.g. background subtraction or truncation of peak angular range) influence the results obtained in peak profile analysis (Langford, 1968). For instance, the peak broadening increases with increasing the width of divergence and receiving slits used in the diffraction instrument (Wilson, 1963; Cheary & Cline, 1994). The contribution of instrumental effects to line broadening should be removed from the measured data in order to obtain the peak profiles caused purely by the microstructure. Both a wrong instrumental correction and a subsequent incorrect evaluation of diffraction peaks may result in systematic errors in the obtained parameters of the microstructure. For instance, when the range of the scattering angle, 2θ , for reflection 111 of cold-worked Ni was smaller

DOI: 10.4018/978-1-5225-1798-6.ch043

than five times the full width at half maximum (FWHM), the mean crystallite size determined from the Fourier transform was significantly smaller than the true value (Langford, 1968). The wrong background subtraction also alters the breadth and shape of peaks used in the evaluation procedures and therefore yields deviation from the true values of the crystallite size or the defect densities. Thus, besides the theory of X-ray line profile analysis some practical skills should also be known in order to obtain reliable results in peak profile analysis.

X-ray line profile analysis is an indirect method for the determination of the microstructure, therefore the evaluation of peak profiles and the interpretation of the results should be performed carefully. Usually, a reliable model of the microstructure is necessary for a correct evaluation of the profile shape (Ungár, Gubicza, Ribárik, & Borbély, 2001), which can be constructed with the help of complementary methods, such as transmission electron microscopy (TEM). However, the parameters of the microstructure determined from line profiles often differ from those obtained by other methods (e.g. by TEM), as the various experimental procedures study the microstructure from different aspects (Gubicza & Ungár, 2007; Samadi Khoshkhoo, Scudino, Thomas, Gemming, Wendrock, & Eckert, 2013). Thus, the viewpoint of line profile analysis in investigation of microstructure and the limits of this method in practice should be known. In this chapter useful practical considerations are presented in order to facilitate the evaluation of peak profiles and the interpretation of the obtained results. The microstructure parameters determined by line profile analysis are compared to the values obtained by microscopic methods.

INSTRUMENTAL CORRECTION

According to the kinematical scattering theory, for an infinite single crystal without any lattice distortions the Bragg peaks are Dirac-delta functions with infinitesimal breadth. The peak broadening decreases with increasing the size of crystallites and decreasing the lattice defect densities, but even for a very large perfect crystal the line breadth goes to a finite value which is referred to as Darwin width (Warren, 1990). In the practice, the peak broadening for a large perfect crystal can be further increased by instrumental effects. The most important factors influencing the shape and breadth of the instrumental peak profiles are (i) the size of X-ray source, (ii) the equatorial and axial divergences of the beam (observed parallel and perpendicular, respectively, to the plane of the incident and diffracted beams), (iii) the width of the receiving slit, (iv) the specimen transparency, (v) the distribution of wavelength of the incident beam (spectral dispersion) and (vi) the misalignment of the diffractometer (Cernansky, 2000). The line breadth caused by the instrumental effects is referred to as “instrumental broadening” which should be taken into account in the evaluation of peak profiles. The total instrumental profile is a convolution of the peaks caused by the different instrumental effects listed above. The instrumental peak profiles for a given diffraction setting can be measured on a standard material which has large crystals with small amount of lattice imperfections. Then, these instrumental profiles can be used for instrumental correction in further experiments carried out under the same instrumental conditions. For the determination of the instrumental broadening the most often used material is the LaB_6 standard (Langford & Louer, 1996). Other materials are also used as instrumental standards, such as annealed BaF_2 (Louer & Langford, 1988) and KCl (Scardi, Lutterotti, & Maistrelli, 1994). Besides the large crystallite size and the very small lattice distortions there is an extra advantage of the application of LaB_6 as a line profile standard material, namely it has many peaks distributed more or less equidistantly in the diffraction pattern. The large number of peaks for the standard material is beneficial since the instrumental broadening varies

37 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage:

www.igi-global.com/chapter/practical-applications-of-x-ray-line-profile-analysis/175731

Related Content

Informatics-Based Approaches for Accelerated Discovery of Functional Materials

P. V. Balachandran and J. M. Rondinelli (2016). *Computational Approaches to Materials Design: Theoretical and Practical Aspects* (pp. 192-223).

www.irma-international.org/chapter/informatics-based-approaches-for-accelerated-discovery-of-functional-materials/156830

Digital Technologies and 4D Customized Design: Challenging Conventions With Responsive Design

James I. Novak and Jennifer Loy (2020). *Additive Manufacturing: Breakthroughs in Research and Practice* (pp. 1-24).

www.irma-international.org/chapter/digital-technologies-and-4d-customized-design/232920

Corrosion Inhibition of Mild Steel in Acidic Pickling Baths: Benzoxazepine Derivatives as Acid Corrosion Inhibitors

Otmane Kharbouch, Khadija Dahmani, Fatima El Hajri, Moussa Ouakki, Mouhsine Galai, Hakima Nassali, Said Boukhris and Mohamed Ebn Touhami (2023). *Handbook of Research on Corrosion Sciences and Engineering* (pp. 529-551).

www.irma-international.org/chapter/corrosion-inhibition-of-mild-steel-in-acidic-pickling-baths/323415

Effects of Tool Wear on Surface Roughness and Cutting Force in Thermoplastics Turning

János Farkas, Etele Csanády and Levente Csóka (2018). *International Journal of Materials Forming and Machining Processes* (pp. 1-11).

www.irma-international.org/article/effects-of-tool-wear-on-surface-roughness-and-cutting-force-in-thermoplastics-turning/192156

3D Printing and Supply Chain Management

(2017). *3D Printing and Its Impact on the Production of Fully Functional Components: Emerging Research and Opportunities* (pp. 50-61).

www.irma-international.org/chapter/3d-printing-and-supply-chain-management/182413