Chapter 6 Evaluation Methods of Line Profiles

ABSTRACT

The evaluation procedures of X-ray line profiles are overviewed in this chapter. These methods can be classified into four groups, namely (1) the most simple methods that evaluate only the breadths of diffraction peaks, (2) procedures using the Fourier-transforms of line profiles for the determination of the parameters of microstructures, (3) variance methods evaluating the restricted moments of peaks, and (4) procedures fitting the whole diffraction pattern. The crystallite size distribution and the densities of lattice defects cannot be determined from the peak width alone as the rule of summation of breadths of size, strain, and instrumental profiles depends on their shape. However, the breadth methods can be used for a qualitative assessment of the main origins of line broadening (size, dislocations, planar faults) (e.g. for checking the model of microstructure used in whole powder pattern fitting procedures). The application of Fourier and variance methods is limited if the diffraction peaks are overlapping. In the case of pattern fitting procedures, usually a microstructure model is needed for the calculation of the theoretical fitting functions. The reliability of these methods increases with increasing the number of fitted peaks.

DOI: 10.4018/978-1-4666-5852-3.ch006

Copyright ©2014, IGI Global. Copying or distributing in print or electronic forms without written permission of IGI Global is prohibited.

INTRODUCTION

The main goal of line profile analysis is to determine the parameters of the microstructure (e.g. crystallite size distribution, dislocation density, planar fault probability etc.) from the diffraction peak profiles. The nature of line broadening caused by crystallite size, dislocations and planar faults are essentially different which enables to separate these effects and determine their characteristic parameters. In chapters 2-4 the theory of the line broadening caused by the finite crystallite size, the lattice strains and the planar faults are reviewed and the theoretical profile functions related to these effects are given. On the basis of these functions several methods were elaborated for the extraction of the parameters of the microstructure from peak profiles. In the early years of the history of line profile analysis, mainly the peak breadths are used to determine the average crystallite size and the average lattice strains in the investigated material. The most frequently applied classical method for the evaluation of peak widths is the Williamson-Hall method (Williamson & Hall, 1953). Later, this procedure has been improved to handle the anisotropic strain broadening of line profiles caused by dislocations (Ungár & Borbély, 1996). The strain anisotropy means that the strain broadening component of the peak width is strongly and characteristically dependent on the indices of reflection hkl. Similar improvement has been made on the other very important evaluation procedure referred to as Warren-Averbach analysis (Warren, 1990). The modified version of this method was capable to give the characteristic parameters of the dislocation structure and the planar fault probability besides the crystallite size (Ungár, Ott, Sanders, Borbély, & Weertman, 1998). The procedures mentioned above need more than one diffraction peak for the successful evaluation. However, a single peak method has also been developed which is referred to as variance method (Wilson, 1955; Groma, 1998). This procedure uses the restricted moments of an intensity profile for the determination of the crystallite size and the characteristic parameters of the dislocation structure (Borbély & Groma, 2001; Groma, Tüzes, & Ispánovity, 2013). The latest improvement of the methodology of line profile analysis is the development of pattern fitting methods which was enabled by the increase of the power of computers. There are several line profile fitting procedures for the evaluation of the diffraction pattern of polycrystalline materials such as MAUD (Lutterotti, Matthies, & Wenk, 1999), FULLPROF (Rodríguez-Carvajal, 2001), FOX or MStruct (Matej, Nichtová, & Kuzel, 2008), MWP (Ungár, Gubicza, Ribárik, & Borbély, 2001; Ribárik, Ungár, & Gubicza, 2001), WPPF (Scardi & Leoni, 1999), WPPM (Scardi & Leoni, 2002) and CMWP (Ribárik, Gubicza, & Ungár, 2004; Balogh, Ribárik, & Ungár, 2006; Balogh, Tichy, & Ungár, 2009). It is noted that MAUD and MStruct can also be applied for thin films as they account for thin film absorption correction and asymmetrical diffraction geometry. In the following the most

39 more pages are available in the full version of this document, which may be purchased using the "Add to Cart"

button on the publisher's webpage: www.igi-

global.com/chapter/evaluation-methods-of-line-profiles/99792

Related Content

Engineered Gellan Polysaccharides in the Design of Controlled Drug Delivery Systems

Sabyasachi Maiti (2017). *Materials Science and Engineering: Concepts, Methodologies, Tools, and Applications (pp. 281-308).* www.irma-international.org/chapter/engineered-gellan-polysaccharides-in-the-design-ofcontrolled-drug-delivery-systems/175697

Experimental Study on Surface Integrity, Dimensional Accuracy, and Micro-Hardness in Thin-Wall Machining of Aluminum Alloy

Gururaj Bolarand Shrikrishna N. Joshi (2018). *International Journal of Materials Forming and Machining Processes (pp. 13-31).* www.irma-international.org/article/experimental-study-on-surface-integrity-dimensional-

accuracy-and-micro-hardness-in-thin-wall-machining-of-aluminum-alloy/209711

3D Printing Analysis by Powder Bed Printer (PBP) of a Thoracic Aorta Under Simufact Additive

Hacene Ameddahand Hammoudi Mazouz (2019). *Additive Manufacturing Technologies From an Optimization Perspective (pp. 102-118).* www.irma-international.org/chapter/3d-printing-analysis-by-powder-bed-printer-pbp-of-athoracic-aorta-under-simufact-additive/230137

Challenges of Semantic 3D City Models: A Contribution of the COST Research Action TU0801

Roland Billen, Anne-Françoise Cutting-Decelle, Claudine Métral, Gilles Falquet, Sisi Zlatanovaand Ognen Marina (2017). *3D Printing: Breakthroughs in Research and Practice (pp. 296-305).*

www.irma-international.org/chapter/challenges-of-semantic-3d-city-models/168228

Research Progress on Rheological Behavior of AA7075 Aluminum Alloy During Hot Deformation

Muhammed O.H Amuda, Taiwo F. Lawaland Esther T. Akinlabi (2017). *International Journal of Materials Forming and Machining Processes (pp. 53-96).* www.irma-international.org/article/research-progress-on-rheological-behavior-of-aa7075-

aluminum-alloy-during-hot-deformation/176061