

# Chapter 5

## Trend and Development in Laser Surface Modification for Enhanced Materials Properties

**Muhammed Olawale Hakeem Amuda**

*University of Lagos, Nigeria & University of Johannesburg, South Africa*

**Esther Titilayo Akinlabi**

*University of Johannesburg, South Africa*

### **ABSTRACT**

*This article presents a process review of the commonly available laser surface modification techniques for surface property enhancement. This is reinforced with the specific case treatment of research trends in relation to commonly treated materials. The progression from simple surface modification to the production of components with multifunctional characteristics known as functionally graded material is discussed in combination with emerging research focus on the computational simulation of laser surface modification for optimization of process dynamics.*

### **1. INTRODUCTION**

Many solid materials possess adequate bulk mechanical properties which commend them for a number of applications but this is not usually the case with their surface properties. In most cases, the bulk material lacks good surface characteristics for

DOI: 10.4018/978-1-5225-0329-3.ch005

### ***Trend and Development in Laser Surface Modification***

effective performance for the timescale over which it is presumed fit-for-purpose. Additionally, literature (Krauss, 1992) indicates that surfaces of materials are subjected to greater stresses and more direct environmental impact than the interior; hence, when such aggressive stresses reached a material's resistance limit, surface initiated fracture, fatigue, wear and corrosion failures occur. Therefore, surfaces of materials are usually treated to make them robust to the environment in which they will be used in order to derive maximum benefit. The process of treating the surface of materials to improve their surface functionalities and making them robust to their environment is referred to as surface modification or surface engineering. The process involves treatment of the surface or near-surface regions of a material to permit the surface to perform functions that are distinct from those demanded from the bulk materials (ASM International, 2001; Cotell and Sprague, 1994). Surface modification has a chequered history from the advent of civilization to the present age and it manifests in many forms; but irrespective of the form, however, it involves changing the composition, crystal structure, texture, chemistry and microstructure of the substrate of the bulk material up to certain depth towards creating new features and properties in the surface (Burakowski and Wierzchon, 1999). Some of the benefits of surface modification include improved corrosion and oxidation resistance, improved wear resistance, reduced frictional energy loss, improved fatigue resistance, enhanced electrical/electronic properties, thermal insulation, size restoration, biomedical functionalization, and improving aesthetics (Ansari et al., 2014). Because the motivation for surface modification is very wide so is the spread of the process very wide as well. At one end of the wide spectrum, the depth of modified surface could be very thin between 0.001-1.0 mm and at the other end, overlay surface depth in the range 1- 20 mm are typical (Krauss, 1992). These modification depths are, of course, process specific and thus, each process can only optimise within a specific length scale range. There are several presentations of the process such as ion implantation, nitriding, aluminising, physical vapour deposition (PVD), chemical vapour deposition (CVD), anodising, laser processing, thermal spraying, cold spraying, and liquid deposition methods. The possible range of modification depth in these processes is shown in Figure 1 with ion implantation providing the smallest depth while weld overlay could be in the tens of a millimetre.

Among these several processes, laser surface modification particularly laser deposition has the capacity to provide across the spectrum range (nano to millimetre) of modified surface depth not possible through other processes. Arising from these possibilities which have resulted in a wide range of improved surface properties in treated materials, the growth in laser surface modification process has been exponential in the last three decades; and new application areas are equally emerging (Baker 2010). The process is one of the strong driving forces advancing additive

27 more pages are available in the full version of this document, which may be purchased using the "Add to Cart" button on the publisher's webpage: [www.igi-global.com/chapter/trend-and-development-in-laser-surface-modification-for-enhanced-materials-properties/149839](http://www.igi-global.com/chapter/trend-and-development-in-laser-surface-modification-for-enhanced-materials-properties/149839)

## Related Content

---

### Review of Microstructural and Mechanical Properties of Microwave Welding of Lightweight Alloys

Eshan Goswami, Ashish Kumar Srivastava, Ajay Kumar, Mohd Salman, Mohd Zeeshan Choudhary and Samarthya Shankar Pandey (2023). *Modeling, Characterization, and Processing of Smart Materials* (pp. 185-204).

[www.irma-international.org/chapter/review-of-microstructural-and-mechanical-properties-of-microwave-welding-of-lightweight-alloys/328473](http://www.irma-international.org/chapter/review-of-microstructural-and-mechanical-properties-of-microwave-welding-of-lightweight-alloys/328473)

### Hydrogen Sorption Behaviors on Lithium Doped MIL@53-AI at Non-Cryogenic Temperatures

Madhavi Konni, Manoj Kumar Karnena and Saratchandra Babu Mukkamala (2022). *International Journal of Surface Engineering and Interdisciplinary Materials Science* (pp. 1-10).

[www.irma-international.org/article/hydrogen-sorption-behaviors-on-lithium-doped-mil53-al-at-non-cryogenic-temperatures/302239](http://www.irma-international.org/article/hydrogen-sorption-behaviors-on-lithium-doped-mil53-al-at-non-cryogenic-temperatures/302239)

### Hydrogen Sorption Behaviors on Lithium Doped MIL@53-AI at Non-Cryogenic Temperatures

Madhavi Konni, Manoj Kumar Karnena and Saratchandra Babu Mukkamala (2022). *International Journal of Surface Engineering and Interdisciplinary Materials Science* (pp. 1-10).

[www.irma-international.org/article/hydrogen-sorption-behaviors-on-lithium-doped-mil53-al-at-non-cryogenic-temperatures/302239](http://www.irma-international.org/article/hydrogen-sorption-behaviors-on-lithium-doped-mil53-al-at-non-cryogenic-temperatures/302239)

### Investigation of the Effect of Cutting Conditions and Tool Edge Radius on Micromachining with the Use of the Finite Elements Method

Angelos P. Markopoulos, Christos Hadjicostas and Dimitrios E. Manolacos (2015). *International Journal of Materials Forming and Machining Processes* (pp. 26-37).

[www.irma-international.org/article/investigation-of-the-effect-of-cutting-conditions-and-tool-edge-radius-on-micromachining-with-the-use-of-the-finite-elements-method/126220](http://www.irma-international.org/article/investigation-of-the-effect-of-cutting-conditions-and-tool-edge-radius-on-micromachining-with-the-use-of-the-finite-elements-method/126220)

## Atlas of , E, and TM–EC for Fullerenes Isomers

Fatemeh Koorepazan-Moftakhar, Ali Reza Ashrafi, Ottorino Oriand Mihai V. Putz (2017). *Sustainable Nanosystems Development, Properties, and Applications* (pp. 615-656).

[www.irma-international.org/chapter/atlas-of--e-and-tmec-for-fullerenes-isomers/162099](http://www.irma-international.org/chapter/atlas-of--e-and-tmec-for-fullerenes-isomers/162099)